




Palladium Silver NANOPARTIC



Composition Chart

Stock No: NS6130-07-716

Palladium / Silver Alloys Nanoparticles developed by Heraeus in 1931 have been used for dentistry in applications such as bridges and crowns. Silver/palladium alloys are also used in conductive films and pastes, as well as to make multilayer capacitors. The addition of palladium to silver increases its resistance to tarnishing or the formation of silver sulphide. However, they are not considered tarnish resistant until the composition reaches 60% Palladium/40% Silver. They are also used in AC and DC low current electronic applications, often as contacts. This is because they are ductile and can easily be made into the required shape. However, their use is somewhat restricted due to their high cost.

CAS 7440-22-4 / 7440-05-3

99.9% Purity <10nm **APS**

Gray/Silver Metallic Color

Powder **Form**

Technical Specification

Pd:Ag Molecular Formula 10.9g/cm³ Density 1155-1220°C **Melting Point**

Chemical Composition

Assay 99.9% 02% Pd Ag 98%















in I www.nanoshel.com I sales@nanoshel.com





Application:

Used in bridges and crowns

Used in multilayer capacitors

Used in conductive films and pastes

Used in dentistry

NANOSHEL UK LIMITED Chapel House, Chapel St Cheshire, CW12 4AB United Kingdom

NANOSHEL LLC 3422 Old Capitol Suit 1305 Wilmington DE - 19808 United States

+91 9779 550077, 9779238252

+44 (0) 74 105 488, +44 203 137 5187